

Reaction fire test	FMVSS 302. Test to determine the horizontal burning rate of materials.
Conditioning	23 ± 2 °C - 50 ± 5% r.h. for 24 hours

Specimen identification number	Burn distance [mm]	Time to burn distance [s]	Burning rate [mm/min]
1	254	418	36,5
2	254	325	46,9
3	254	392	38,9
4	254	316	48,2
5	254	288	52,9

The material complies of Directive FMVSS 302 (expiration date 12/2020)